



PRO GOLD WARNING TRACK MIX

1. Pro Gold Warning Track Mix shall consist of 40-60% screened loamy sand to 40-60% Cinder Sand and/or 3/16"-1/8" minus scoria or a combination of both as produced by Gail Materials.
2. Natracil™ organic binder shall be added at a rate of 10-12 lbs/ton as distributed by Gail Materials. Natracil™ organic binder shall have a minimum swell volume of 35 ml/gm and shall be blended with a pug mill that includes a weight belt feeder that insures the proper ratio and the uniform blending of the binder.
3. For installation of new tracks place Pro Gold Warning Track Mix to a depth of 3-4 inches compacted or as specified in construction documents. Placement of Pro Gold Warning Track Mix can be installed over compacted native sub-grade, decomposed granite or as specified in construction documents.
4. To install evenly spread the material in 1-2 inch lift at a time over the entire surface area and apply water so that the entire depth of each lift is thoroughly moist before compacting (do not compact between lifts). Place in lifts until material reaches final grade and can account for shrinkage after compaction (~20% on average). After a period of +/- 6 hours or more compact the final lift with a minimum 2000 lb. static drum roller. Continue to compact and level to final grade, if additional material needs to be added to reach final grade proper scarification of compacted material and blending of new material must be done to avoid layering. Allow for the material to thoroughly dry and cure before activity on the new track surface. It should be noted that for a level surface it is recommended to grade the area with a laser level or similar.
5. Supplier – Gail Materials (951) 667-6106, www.gailmaterials.net

GAIL MATERIALS

10060 Dawson Canyon Road, Corona, CA 92883
(951) 667-6106 • Fax (951) 667-6102

www.gailmaterials.net